

Fecha de Alta

09-07-2007

Versión

11 - 17/11/2025



FAMILY PAREDES Y TECHOS

LINE ANTIMANCHAS

DESCRIPTION AND NATURE

Solvent base insulating paint. Specifically formulated to remove and eliminate diverse stains and smoke. Odourless.

USAGES

Indoors
Concrete
Spotted smoke, nicotine, oil
Plaster
Smoke, nicotine

PROPERTIES

Adherence
Anti-spots
Optimal applicability
Penetrating depth
No sanding necessary for repainting. Non expensive maintenance
It controls absorption
Odourless when dry

TECHNICAL CHARACTERISTICS

Referencia Color	TIXOWAY ANTIMANCHAS
Finish	Matt
Specific weight	1,4 ± 0,05 kg/l
Viscosity	133 +/- 15 PO
Solids in volume	40 ± 1
Solids in weight	68 ± 1
VOC	Cat. i/BD 600/500 (2007/2010): 489,76 g/l
Aproximated performance by coat	3-6 m ² /L
Dry to touch	(20°C HR: 60%): 90-120min
Dry to repaint	(20°C HR: 60%): >24h
Colours	White

SURFACE PREPAIRING

New surfaces

Cement mortar:

- Wait till complete drying of product (30 days minimum).
- Surface should be totally dry (maximum 20% moisture content).
- Remove off any efflorescences and neutralize alkaline surfaces.
- Extremely polished surfaces should be sanpapered to open pores.
- Remove off any foreing products or remains.
- Only apply product on dry and free of dust surfaces
- Cover surface imperfections with suitable plaster (See Family 6 to help you choose the most suitable product to prepare surfaces).
- For extreme cases with anchoring problems, apply Fijalite.

New wood:

Fecha de Alta

09-07-2007

Versión

11 - 17/11/2025

- Surface should be free of any foreign products or remains.

Iron or steel:

- Remove surface off any rust, grease or dirt and prime with Antioxidante Blanca (ref. 1800) or MINIO DE PLOMO MARINO (ref.1810).

Restoring and maintenance

- Old paint in bad condition and with poor adhesion should be removed.
- Product should be applied directly on oil, grease, nicotine or smoke stains.
- Extreme cases should be previously cleaned with hot water and detergents.
- Leave to dry and proceed to paint.

WAY OF USE

Application notes

- Shake product until perfectly homogenized.
- Follow application guidelines as shown on table below.
- Optimal results can be obtained with one single coat of Tixoway Antimanchas, however, extreme cases may need a second coat.
- Do not apply product at high temperatures or on overheated surfaces exposed to sunshire.
- Do not apply when moisture content is over 80%.
- Keep room well ventilated while product is drying.
- No need to finish with plastic paints. In case of carrying out this operation, never before 7 days.

Solvent for dilution and cleaning

Solvent 1412, 1401, 1402, 1405, Simil Aguarrás

Way of use	Aproximate dilution
Painting brush	al uso
Roller	al uso
Air-less gun	10-25%
Air-mix gun	10-25%
Aerographic gun	10-25%
Low pressure turbo	10-25%

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Metal decoration			
MAX	Imprimación Antioxidante blanca	Tixoway Antimanchas	Tixoway Antimanchas
STD	Minio de Plomo		Tixoway Antimanchas
Inner painted old work in good state			
MAX	Tixoway Antimanchas		Tixoway Antimanchas
STD	Tixoway Antimanchas		Tixoway Antimanchas
Inner painted old work in good state			
MAX	Primer Montolite ó Fijamont	Tixoway Antimanchas	Tixoway Antimanchas
STD	Primer Montolite ó Fijamont		Tixoway Antimanchas
New work			
MAX	Primer Montolite ó Fijamont	Tixoway Antimanchas	Tixoway Antimanchas
STD	Tixoway Antimanchas		Tixoway Antimanchas
Paints with stains			
MAX	Tixoway Antimanchas		Tixoway Antimanchas

Fecha de Alta

09-07-2007

Versión

11 - 17/11/2025

STD Tixoway Antimanchas

Tixoway Antimanchas

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances.As it is impossible to stablish an adecuate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.75 L, 4 L, 15 L



FAMILY LINE

DESCRIPTION AND NATURE

Solvent base insulating paint. Specifically formulated to remove and eliminate diverse stains and smoke. Odourless.

USAGES

PROPERTIES

Adherence
Anti-spots
Optimal applicability
Penetrating depth
No sanding necessary for repainting. Non expensive manteinance
It controls absorption
Odourless when dry

TECHNICAL CHARACTERISTCS

Referencia Color

Finish	Matt
Specific weight	1,4± 0,05 kg/l
Viscosity	133 +/- 15 PO
Solids in volume	40± 1
Solids in weight	68± 1

Fecha de Alta

09-07-2007

Versión

11 - 17/11/2025

VOC	Cat. i/BD 600/500 (2007/2010): 489,76 g/l
Aproximated performance by coat	3-6 m ² /L

Dry to touch	(20°C HR: 60%): 90-120min
Dry to repaint	(20°C HR: 60%): >24h
Colours	White

SURFACE PREPARING

New surfaces

Cement mortar:

- Wait till complete drying of product (30 days minimum).
- Surface should be totally dry (maximum 20% moisture content).
- Remove off any efflorescences and neutralize alkaline surfaces.
- Extremely polished surfaces should be sanpapered to open pores.
- Remove off any foreing products or remains.
- Only apply product on dry and free of dust surfaces
- Cover surface imperfections with suitable plaster (See Family 6 to help you choose the most suitable product to prepare surfaces).
- For extreme cases with anchoring problems, apply Fijalite.

New wood:

- Surface should be free of any foreign products or remains.

Iron or steel:

- Remove surface off any rust, grease or dirt and prime with Antioxidante Blanca (ref. 1800) or MINIO DE PLOMO MARINO (ref.1810).

Restoring and maintenance

- Old paint in bad condition and with poor adhesion should be removed.
- Product should be applied directly on oil, grease, nicotine or smoke stains.
- Extreme cases should be previously cleaned with hot water and detergents.
- Leave to dry and proceed to paint.

WAY OF USE

Application notes

- Shake product until perfectly homogenized.
- Follow application guidelines as shown on table below.
- Optimal results can be obtained with one single coat of Tixoway Antimanchas, however, extreme cases may need a second coat.
- Do not apply product at high temperatures or on overheated surfaces exposed to sunshine.
- Do not apply when moisture content is over 80%.
- Keep room well ventilated while product is drying.
- No need to finish with plastic paints. In case of carrying out this operation, never before 7 days.

Solvent for dilution and cleaning

Solvent 1412, 1401, 1402, 1405, Simil Aguarrás

Way of use	Aproximate dilution
Painting brush	al uso
Roller	al uso
Air-less gun	10-25%
Air-mix gun	10-25%
Aerographic gun	10-25%
Low pressure turbo	10-25%

Fecha de Alta

09-07-2007

Versión

11 - 17/11/2025

SYSTEM**Procedures depending of surface type**

	Primer	Intermedium	Finish
Metal decoration			
MAX	Imprimación Antioxidante blanca	Tixoway Antimanchas	Tixoway Antimanchas
STD	Minio de Plomo		Tixoway Antimanchas
Inner painted old work in good state			
MAX	Tixoway Antimanchas		Tixoway Antimanchas
STD	Tixoway Antimanchas		Tixoway Antimanchas
Inner painted old work in good state			
MAX	Primer Montolite ó Fijamont	Tixoway Antimanchas	Tixoway Antimanchas
STD	Primer Montolite ó Fijamont		Tixoway Antimanchas
New work			
MAX	Primer Montolite ó Fijamont	Tixoway Antimanchas	Tixoway Antimanchas
STD	Tixoway Antimanchas		Tixoway Antimanchas
Paints with stains			
MAX	Tixoway Antimanchas		Tixoway Antimanchas
STD	Tixoway Antimanchas		Tixoway Antimanchas

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE**PACKINGS**

0.75 L, 4 L, 15 L