



CORROLUX antirust

Gloss Antirust Enamel



Covering Power: 15-17 m²/lt



Drying: 1 - 3 hours



Dilution:

Up to 5% on volume with Smaltolux White spirit

Up to 8% on volume with Thinner No1



Recoatability: 18 hours



Packing: 750ml , 2,5lt



Application: Brush, Roller, Spraygun

GENERAL CHARACTERISTICS

Special gloss anticorrosive alkyd enamel, suitable for new and for old surfaces. The product can be applied direct to rust! Ideal for renovation of old surfaces. Value for money. It gives very good adhesion, flow, leveling and fast drying.

TECHNICAL CHARACTERISTICS

Texture	Gloss, 84-88 units in 60°.
Specific weight	1,18 - 1,21 kg/lt (White). 0,98 - 1,00 kg/lt (Black). 1,00 - 1,20 kg/lt (Shades).
Covering Power	15-17 m ² /lt per layer depending on the surface.
Dilution	Up to 5% on volume with SMALTOLUX WHITE SPIRIT for application by brush or roller and up to 12% with Thinner No1 of VECHRO for spray application.
Drying	1-3 hours touch free depending on the surface.
Recoatability	Recoatable 18 hours after application or after first layer' s hardening. These times prolong under cold and wet weather conditions..
VOC class	“One-pack performance coatings. Anticorrosion finishes” Type SB. VOC limit =500 gr/lt. Max VOC of product ready for use= 485 gr/lt. VOC: organic volatile compounds with boiling point < 250 °C.
Antirust protection	At 240 hours (10 days) salting, the product at a dry film thickness of 100 microns exhibits excellent handling.
Shades	White, black and ready-made shades of VECHRO.



SURFACE PREPARATION

Clean the surface of dust, oil, cropped paints, rust. Sandpaper well and clean the surface with SMALTOLUX WHITE SPIRIT.

APPLICATION

Stir well. Apply one or two coats CORROLUX (film thickness 80-120 μm) for better anticorrosive protection. Be sure that the whole of surface has been well coated.

CLEANING EQUIPMENT

While working keep your equipment wet, either in the pot, or in the paint lauder. Strain well your tools from paint back to the pot and clean immediately with warm water and soap.

APPLICATION CONDITIONS

Temperature 8-30 $^{\circ}\text{C}$ and relative humidity lower than 80%. Contrary weather conditions may degrade paint's quality.

STORAGE

Close well after use. Store in a cool place. Protect from sun exposure.

LABELLING

More information in Material Safety Data Sheet (MSDS) .

SAFETY

Read the tag on the back side of the product. Keep out of the reach of children.



The technical data and instructions included in this technical leaflet are based on audits of confidential laboratories and result of the knowledge and experience of the company's scientific staff. The quality of the product is guaranteed by the company, which is aligned with the requirements of ISO 9001, 14001 and EMAS. As a producer, we are not responsible for any damage or damage caused if the product has not been used for proper application and in accordance with its instructions for use.